

TYGON® 3370 I.B. Braid-Reinforced Silicone Hose



Designed to Maintain Fluid Purity Under Pressure

Braid reinforced for increased pressure resistance, TYGON® 3370 I.B. silicone hose is frequently specified in the most demanding applications requiring sanitary transfer of fluids. Its smooth inner surface reduces the risk of particle entrapment and inhibits microscopic bacterial build-up. Cleaning and sterilization cycles also may become more effective from this smooth inner surface by helping to prevent excessive residue build-up during use. Additionally, an improvement in fluid flow characteristics may occur from the reduced surface area and lowered absorption of fluids to the wall.

TYGON 3370 I.B. can easily withstand repeated SIP and CIP cleaning and sterilization cycles, making it ideal for repeat-use applications. Its flexibility, durability, chemical and temperature resistance provide a unique combination of characteristics required in many pharmaceutical, biotechnology, laboratory, food, beverage, cosmetic, environmental, and industrial applications.

Lower Extractables and Exceptional Biocompatibility

TYGON 3370 I.B. silicone hose is produced from a platinum curing process to meet the most demanding requirements of biocompatibility.

In-house extractability tests have shown that TYGON 3370 I.B. hose has a low extractable content. Lower extractables help to maintain the purity of transported fluids in sensitive applications.

TYGON 3370 I.B. hose complies fully with the requirements of the USP Class VI Criteria and is entirely non-toxic, non-hemolytic and non-pyrogenic. Continued monitoring of the hose also ensures minimal bioburden levels are maintained. TYGON 3370 I.B. hose also meets 3-A Sanitary Standard No. 18-01 and FDA 21 CFR Part 177.2600 Criteria.

BIOPHARMACEUTICAL PRODUCTS

The smooth surface, platinum-cured silicone hose designed for transferring high-purity fluid under pressure

Features/Benefits

- Consistently Smooth Inner Surface Limits Particle Entrapment
- Platinum Cured to Minimize Extractables
- Tough Braid Reinforcement Permits Use Under Elevated Working Pressures
- Withstands Repeated CIP and SIP Cleaning and Sterilization
- Custom Color Striping Available

Typical Applications

- Sterile Filling
- Media Dispensing
- Vaccine Manufacturing
- Bioreactor Process Lines
- Water Purification Systems
- Food and Dairy Processing
- Diagnostic Test Product Manufacturing
- Sanitary Fitting Assembly

TYGON® 3370 I.B. Hose Inventory Sizes

Part Number	I.D. (inches)	O.D. (inches)	Minimum Bend Radius	Length (feet)	Max. Working Pressure		Vacuum Rating In. of Mercury	
					at 73°F (psi) *	at 160°F (psi)*	at 73°F	at 160°F
AHJ001718	3/16	.443	1/4	50	170	125	29.9	29.9
AHJ001719	1/4	.515	1/2	50	150	105	29.9	29.9
AHJ001720	3/8	.687	3/4	50	130	95	29.9	29.9
AHJ001721	1/2	.847	1-1/4	50	125	90	29.9	29.9
AHJ001722	5/8	.980	1-1/2	50	110	80	29.9	29.9
AHJ001671	3/4	1.150	2-1/4	50	100	75	29.9	29.9
AHJ001724	1	1.390	3-1/2	50	70	50	15.0	10.0
AHJ421725	1-1/4	1.636	5-3/4	25	55	40	10.0	5.0
AHJ421726	1-1/2	1.900	6-3/4	25	40	30	5.0	0.0

*Working pressures are calculated at a 1.5 ratio relative to burst pressure using ASTM D1599.

The values listed for working and burst pressures are derived from tests conducted under controlled laboratory conditions. Many factors will reduce the hose's ability to withstand pressures, including temperature, chemical attack, stress, pulsation and the attachment to fittings. It is imperative that the user conduct tests simulating the conditions of the application prior to specifying the hose for use.

TYGON® 3370 I.B. Typical Physical Properties

Property	ASTM Method	Value or Rating
Durometer Hardness Shore A, 15 Sec	D2240-91	70
Color	—	Translucent
Tensile Strength psi (MPa)	D412-92	1,200 (8.3)
Ultimate Elongation, %	D412-92	500
Tear Resistance lb-f/inch (kN/m)	D624-91 Die B	250 (44)
Specific Gravity	D792-91	1.18
Water Absorption, % 24 hrs. @ 23°C	D570-81	0.11
Compression Set Constant Deflection, % @ 158°F (70°C) for 22 hrs. @ 347°F (175°C) for 22 hrs.	D395-89 Method B	3 10
Brittleness by Impact Temp., °F (°C)	D746-79	-112 (-80)
Maximum Recommended Operating Temp., °F (°C)	—	320 (160)
Dielectric Strength v/mil (kV/mm)	D149-93	600 (24)
Tensile Modulus, 200% psi (MPa)	D412-92	650 (4.5)
Tensile Set, %	D412-92	25

Unless otherwise noted, all tests were conducted at roomtemperature (73°F). Values shown were determined on 0.075" thick extruded strip or 0.075" thick molded ASTM plaques or molded ASTM durometer buttons.

TYGON HOSE IS NOT INTENDED FOR USE AS AN IMPLANT MATERIAL

TYGON® 3370 I.B. Toxicological Profile

The biocompatibility of TYGON 3370 I.B. has been tested and found to be non-toxic in the following test protocols:

USP Systemic Toxicity and Intracutaneous Reactivity
 USP Intramuscular Implant
 Cytotoxicity
 Blood Compatibility
 USP Physico Chemical Tests

TYGON® 3370 I.B. Sterilization Methods

Autoclavable — Steam 30 minutes at 15 psi (250°F)
 Gas — Ethylene Oxide
 Radiation — Radiation up to 2.5 MRad

TYGON® is a registered trademark.

BIOPHARMACEUTICAL PRODUCTS

Come through clean.™

Saint-Gobain Performance Plastics

3910 Industrial Drive
 Beaverton, MI 48612
 Tel: (989) 435-9533
 Tel: (888) 387-0067
 Fax: (989) 435-2355



IMPORTANT: It is the user's responsibility to ensure the suitability and safety of Saint-Gobain Performance Plastics tubing for all intended uses. Laboratory and clinical tests must be conducted in accordance with applicable regulatory requirements in order to determine the safety and effectiveness for use of tubing in any particular application.

For a period of 6 months from the date of first sale, Saint-Gobain Performance Plastics Corporation warrants this product to be free from defects in materials and workmanship. Our only obligation will be to replace any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risk, if any, including the risk of injury, loss or damage, direct or consequential, arising out of the use, misuse, or inability to use, this product. THIS WARRANTY IS IN LIEU OF THE WARRANTIES OF MERCHANTABILITY, FITNESS FOR PARTICULAR PURPOSE, AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED. No deviation is authorized.

Saint-Gobain Performance Plastics Corporation assumes no obligations or liability for any advice furnished by it, or for results obtained with respect to those products. All such advice is given and accepted at the buyer's risk.